

SERIES T 25

Technical Data Sheet

Pad printing inks

1. APPLICATION FIELDS:

One-component printing ink for pad printing on non-pre-treated polypropylene (PP). Substrates may differ in their chemical structure or method of manufacture. A test for suitability must always be carried out before printing. Antistatic, Mould Release Agents and Slip Additives may have negative effects on adhesion and should be detected and removed prior to printing.

2. CHARACTERISTICS:

This glossy, physically drying pad printing ink exhibits good mechanical and chemical resistance. The inks of T25 are light fast, weather resistant and guarantee high opacity. Oil resistance can only be achieved in a limited manner. A special product test is recommended prior to production.

3. RANGE OF COLOURS:

The basic ink mixing system consists of 12 basic colours and may be used for the mixing of a wide colour shade range.

3.1 Basic Colours:

Light Yellow	B 1	T25-2003
Medium Yellow	B 2	T25-2004
Orange	B 3	T25-3002
Light Red	B 4	T25-3003
Red	B 5	T25-3004
Pink	B 6	T25-3005
Violet	B 7	T25-5007
Blue	B 8	T25-5008
Green	B 9	T25-6000
White	B 11	T25-1001
Black	B 12	T25-9001
Clear Base		T25-0001

3.2 Special Products:

3.2.1 Opaque Formulations:

White	T25-1002
Black	T25-9002
Yellow	T25-2005
Red	T25-3006

4. ADDITIVES:

4.1 Thinner:

Prior to production the pad printing ink is adjusted to the printing viscosity by the addition of thinner.

Following additives are available:

Thinner, standard	(addition 10 - 20%)	100VR1370
Thinner, fast	(addition 10 - 20%)	38571

The retarder VZ 35928 can be used in order to achieve a medium drying retardation.

Retarder	(max. addition 5%)	35928
----------	--------------------	-------

4.2 Levelling Agent:

The levelling of the ink surface can be optimised by the use of levelling agent. It must be noted that excessive addition of levelling agent can have a negative influence on the overprintability.

Levelling Agent	(max. add.: 0,5 - 1 %)	100VR133
-----------------	------------------------	----------

4.3 Cleaning Agent:

In some cases, it may be advisable to remove dust and other impurities off the PP surface prior to printing by means of the cleaning liquid 35352 or with other suitable cleaning agents in order to enhance the adhesion properties of the ink.

Cleaning Agent	35352
----------------	-------

5. PROCESSING INSTRUCTIONS:

5.1 Cliché / Printing Equipment / Pad:

The T25 series can be used with all pad printing machines with clichés and pads currently used for industrial applications. However, it has to be noted that type (screen) and etching depth of the cliché, mould and hardness of the pad, the adjustment of the ink (addition of thinner and/or retarder) as well as printing speed may influence the printing result.

5.2 Drying Conditions:

The drying properties of the pad printing ink during the printing process have a decisive meaning for the printing result. An optimal ink transfer can be achieved if - due to solvent evaporation - a superficial drying of the ink first inside of the cliché and afterwards on the pad is guaranteed. Under these circumstances the total ink quantity will be transferred from the pad to the substrate.

SERIES T25

At processing temperatures of more than 25°C and at low printing speeds a drying of the ink in the cliché may happen. Not all parts of the image area will be transferred.

At room temperature (21°C) the inks of T25 series are grip dry within 2 – 3 minutes. To accelerate the ink drying onto the substrate the use of hot air blower or infra red lamps is recommended. It must be noted that after heat treatment a cooling section must be installed in order to avoid that the printed parts stick together.

6. CLEANING:

Clichés, squeegees and so on can be cleaned with the **RUCOINX** Universal cleaner 100VR1272. It must be noted that the pad does not come into contact with solvents. For the cleaning of the pad please see to the application references of the pad manufacturers.

If cleaning is not performed by fully automatic cleaning equipment, protective gloves must be worn.

Biodegradable Cleaner 100VR1272

7. SHELF LIFE:

A shelf life of 36 months is guaranteed when storing the inks at 21 °C and in the original packing container. At higher storage temperatures the shelf life will be reduced.

8. PRECAUTIONS:

For further information on the safety, storage and environmental aspects concerning these products please refer to the Material Safety Data Sheet (MSDS).

Additional technical information may be obtained from our staff of the Product Management Department.

A. M. RAMP & Co. GmbH
RUCOINX Druckfarben
Lorsbacher Straße 28
65817 Eppstein/Ts.
Germany

Phone: +49 (0) 6198-304-0
Fax: +49 (0) 6198-304-3 22 88
E-Mail: info.de@inx europe.com
www.ruco-inks.com
www.inx europe.com

