# 

UV screen printing inks

# SERIES 985UV/NV

# **Technical Data Sheet**

### 1. APPLICATION FIELDS:

Universal low viscosity UV screen printing ink for printing on plastic foils, especially in rotation screen printing procedures, suitable for pre-treated substrates made of polyolefins, polyethylene (PE), polypropylene (PP), Primer precoated polyester, PVC and other plastic types as well as for printing on paper and cardboard.

Substrates may differ in their chemical structure or method of manufacture. A test for suitability must always be carried out before printing. Antistatic, Mould Release Agents and Slip Additives may have negative effects on adhesion, and should be detected and removed prior to printing.

#### 2. CHARACTERISTICS:

This high gloss UV ink series is very reactive in nature, assuring good curing and adhesion even when printing at high machine speeds. The inks of the 985UV/NV series are constitutionally free from toxic elements and solvents.

The inks of this series feature good solvent and water resistance after 12 hours.

This ink series is *not* suitable for printing onto food packaging.

#### 3. RANGE OF COLOURS:

The basic ink mixing system consists of 12 basic colours and may be used for the mixing of a wide colour shade range. Field proven mixing formulations exist for Pantone<sup>®</sup>, HKS, RAL, NCS, etc.

#### 3.1 Basic colours:

Light Yellow	G 1	985UV2391NV
Medium Yellow	G 2	985UV2392NV
Orange	G 3	985UV3764NV
Light Red	G 4	985UV3765NV
Red	G 5	985UV3766NV
Pink	G 6	985UV3767NV
Violet	G 7	985UV5831NV
Blue	G 8	985UV5832NV
Green	G 91	985UV6662NV
White	G 11	985UV1152NV
Black	G 12	985UV9145NV
Clear Base		985UV0069NV

#### 3.2 Euro-Colours / 4-Colour Set Printing Inks:

For 4-colour set printing according to DIN 16538, 4 process colours are available:

Process-Yellow	985UV2674NV
Process-Magenta	985UV3854NV

Process-Cyan Halftone Black 985UV5885NV 985UV9179NV

#### 3.3 Bronze Colours:

See separate "Bronze Colours" leaflet

#### 4. ADDITIONAL PRODUCTS:

The high reactive UV transparent paste can be used to reduce the colour density.

Raster paste can be added to reduce "Dot Gain" and to achieve sharper dots for half tone printing.

Printing Lacquer		985UV0094NV
Transparent Paste	(max. addition 10%)	985UV0124NV
Raster Paste	(max. addition 10%)	985UV0012NV

#### 5. ADDITIVES:

#### 5.1 UV-Thinner:

The inks of the 985UV/NV series are ready to use. If the viscosity needs to be adjusted, a UV-thinner may be added. In order to increase the curing we recommend adding reactive thinner.

In general, no solvent-based thinners should be used to avoid damages of the equipment and because of their explosion risk.

UV-Thinner	(max. addition 2-5%)	985UV0014
Reactive-Thinner	(max. addition 2-5%)	985UV0010

#### 5.2 Adhesion Modifiers:

In the case of particularly high resistance requirements, we recommend the addition of an adhesion modifier. However the addition of adhesion modifier to UV curable ink will lead to a processing time (pot life) of 4-8 hours at 21°C depending on the colour shade. Higher processing temperatures will result in a shorter pot life.

Overprinting must take place within 12 hours at 21°C in case an adhesion modifier is added.

Adhesion Modifier (addition 2%-4%) 100VR1491

#### 5.3 Levelling Agent:

The levelling of the ink surface can be optimised by the use of a levelling agent.

Levelling Agent (max. addition 0,5-1%) 100VR1297

The above statements are accurate to our best knowledge and belief. However, due to the great number of possible influences during the manufacture of the substrate and the variation in the application process we suggest that suitability testing take place under actual conditions before production. No legally binding guarantee of certain properties or of the suitability for a definite application purpose can be derived from the above information. TDS\_985UV/NV\_EN\_20210623-20

# SERIES 985UV/NV

#### 6. PROCESSING INSTRUCTIONS:

#### 6.1 Pre-treatment:

Pre-treatment of polyolefins (PE/PP) must be performed by Flame Treatment or CORONA-discharge in order to insure the adhesion of the UV screen printing ink to the substrate. In case of PE, surface tension needs to be at least 42 mN/m (Dynes/cm), in case of PP at least 52 mN/m (Dynes/cm).

#### 6.2 Stencils / Printing Equipment:

Suitable mesh types are: RotaMesh<sup>®</sup> RM 305/17%, RM 305/13% or mesh type Screeny<sup>®</sup> KM 325/22% and KS 325/25% which are used on rotary screen printing machines.

The colour mixing formulations are based on a 165-34 threads/cm mesh. However, we generally recommend test prints and approval of the colour for the respective print jobs.

Any acrylic acid ester resistant squeegee material may be used.

#### 6.3 Curing Conditions:

The varying UV absorption of the individual colours results in a range of curing properties depending on colour and opacity. All colours of the 985UV/NV series can be cured by the use of medium pressure mercury vapour lamps (at least 160 W/cm). The optimum energy output is 250 - 300 Millijoule/cm<sup>2</sup>. UV curing is followed by a 12 hour post-cure phase after which the ink film is fully cured and has its final properties. However, it must be noted, that low radiation intensity, excessive machine speeds or excessive film thickness can have a negative influence on the curing properties and adhesion.

Un-cured prints are considered a hazardous waste. Therefore, we recommend curing misprints under the UV lamp as a matter of principle. After curing, spoilage can be disposed by conventional methods and may be incinerated without causing any difficulties.

## 7. CLEANING:

Screens and squeegees as well as other working materials can be cleaned with the RUCO screen cleaner 32335. If cleaning is not performed by fully automatic cleaning equipment, protective gloves must be worn. Cleaning liquids that are contaminated with UV products should not be used for the washing of working materials that were used with conventional screen printing inks. Solvents that contain UV residue are not suitable for reclamation and must be treated as a separate waste.

Universal Cleaner	32335
Cleaner for cleaning equipment	100VR1240C
Bio degradable Cleaner	100VR1272

## 8. SHELF LIFE:

A shelf life of 12 months is guaranteed when storing the inks at 21°C and in the original packing container. At higher storage temperatures the shelf life will be reduced.

#### 9. PRECAUTIONS:

UV inks may cause irritations and can increase the sensitivity of the skin, possibly leading to hypersensitivity. Therefore, the use of disposable gloves and protective goggles is strongly recommended.

For further information on the safety, storage and environmental aspects concerning these products please refer to the Material Safety Data Sheet (MSDS).

Additional technical information may be obtained from our staff of the Product Management Department.

A. M. RAMP & Co. GmbH Lorsbacher Strasse 28 D-65817 Eppstein

Tel: +49 (0) 6198-304-0 FAX: +49 (0) 6198-304-287 E-Mail: <u>info@ruco-inks.com</u> www.ruco-inks.com



The above statements are accurate to our best knowledge and belief. However, due to the great number of possible influences during the manufacture of the substrate and the variation in the application process we suggest that suitability testing take place under actual conditions before production. No legally binding guarantee of certain properties or of the suitability for a definite application purpose can be derived from the above information. TDS\_985UV/NV\_EN\_20210623-20