



SERIES 950UV



Technical Data Sheet

UV screen printing inks

1. APPLICATION FIELDS:

UV screen printing ink for the printing of blow moulded objects suitable for substrates made of polyolefins, especially for polyethylene (PE) tubes.

Substrates may differ in their chemical structure or method of manufacture. A test for suitability must always be carried out before printing. Antistatic, Mould Release Agents and Slip Additives may have negative effects on adhesion and should be detected and removed prior to printing.

2. CHARACTERISTICS:

The inks of series 950UV are formulated with special organic pigments. Out of it the good opacity, high colour intensity and good light-fastness result. The inks are of high reactivity and offer flexible ink films and can be easily overprinted and over-lacquered. They are not suitable for the overprinting of ink films containing silicone (like the ink series 985 UV for example).

The inks of this series will exhibit good solvent and water resistance after 12 hours.

The inks of the 950UV series are constitutionally free from toxic elements and solvents.

The used raw materials also comply with the limits of metal elements stipulated by the actual EEC regulation *EN 71-3 (Safety of Toys), part 3* (Migration of Certain Elements).

This ink series is *not* suitable for printing onto food packaging.

For Gold- and Silver as well as Metallic inks it is recommended to proof if the thresholds for aluminum, copper and zinc are respected.

3. RANGE OF COLOURS:

The basic ink mixing system consists of 11 basic colours and may be used for the mixing of a wide colour shade range. We offer computer based mixing formulations which can be taken as a basis for the matching of the varying printing conditions such as screens and the differently dyed substrates.

3.1 Basic Colours:

Yellow	D 1	950UV2866
Yellow reddish	D 2	950UV2867
Orange	D 3	950UV30791
Light Red	D 4	950UV30792
Red	D 5	950UV30793
Pink	D 6	950UV30794
Violet	D 7	950UV50963
Blue	D 8	950UV50964
Green	D 9	950UV60290
White	D 11	950UV1292

Black	D 12	950UV9260
Clear Base		950UV0007

3.2 Special Formulations:

The special formulations are additional colour shades which can be used in case of particular requirements with regard to the opacity.

3.2.1 High Opacity Formulations:

Blue, D 85	(high opacity)	950UV50965
White	(high opacity)	950UV1295

3.2.2 Printing Black:

Printing Black	950UV9262
----------------	-----------

4. ADDITIVES:

4.1 UV-Thinner:

The inks of the 950UV series are ready to use. If further viscosity reduction is desired, UV-thinner may be added. In order to increase curing, the addition of reactive thinner is recommended.

In general, no solvent-based thinners should be used due to flammable nature of the solvents.

UV-Thinner	(max. addition 2 - 5 %)	950UV0014
Reactive-Thinner	(max. addition 2 - 5 %)	950UV0010

4.2 Adhesion Modifier:

In the case of particularly high resistance requirements, the addition of adhesion modifier is recommended. However the addition of adhesion modifier to UV curable ink will lead to a processing time (pot life) of 4 - 8 hours at 21 °C depending on the colour shade. Higher processing temperatures will result in a shorter potlife.

Overprinting must take place within 12 hours at 21 °C in case an adhesion modifier is added.

Adhesion Modifier	(addition 2 % - 4 %)	100VR1491
-------------------	----------------------	-----------

4.3 Levelling Agent:

The levelling of the ink surface can be optimised by the use of a levelling agent.

Levelling Agent	(max. addition 0.5 % - 1 %)	900UV-VM
-----------------	-----------------------------	----------

SERIES 950 UV

5. PROCESSING INSTRUCTIONS:

5.1. Pre-treatment:

Pre-treatment of polyolefins (PE/PP) must be performed by flame treatment or CORONA-discharge in order to insure the adhesion of the UV screen printing ink to the substrate. In case of PE, surface tension needs to be at least 42 mN/m (Dynes/cm), in case of PP at least 52 mN/m (Dynes/cm).

5.2 Stencils / Printing Equipment:

Screen printing meshes between 120 - 31 threads/cm and 165 - 27 threads/cm are suitable for printing with UV inks.

However, test prints and approval of the colour are generally recommended for the respective print jobs.

The 950UV series can be used with all screen printing machines with screen printing stencils currently used for industrial applications.

Any acrylic acid ester resistant squeegee material may be used.

5.3 Curing Conditions:

The varying UV absorption of the individual colours results in a range of curing properties depending on colour and opacity. All colours of the 950UV series can be cured by the use of medium pressure mercury vapour lamps (at least 160 W/cm).

The optimum energy output is 100 - 200 Millijoule/cm². UV curing is followed by a 12 hour post-cure phase after which the ink film is fully cured and has its final properties.

However, it must be noted, that low radiation intensity, excessive machine speeds or excessive film thickness can have a negative influence on the curing properties and adhesion.

Un-cured prints are considered a hazardous waste. Therefore, it is recommended to cure misprints under the UV lamp as a matter of principle. After curing, spoilage can be disposed by conventional methods and may be incinerated without causing any difficulties.

6. CLEANING:

Screens and squeegees as well as other working materials can be cleaned with the **RUCOINX** screen cleaner 1272. If cleaning is not performed by fully automatic cleaning equipment, protective gloves must be worn. Cleaning liquids that are contaminated with UV products should not be used for the washing of working materials that were used with conventional screen printing inks. Solvents that contain UV residue are not suitable for reclamation and must be treated as a separate waste.

Bio degradable Cleaner

100VR1272

7. SHELF LIFE:

A shelf life of 24 months is guaranteed when storing the inks at 21 °C and in the original packing container. At higher storage temperatures the shelf life will be reduced.

8. PRECAUTIONS:

UV inks may cause irritations and can increase the sensitivity of the skin, possibly leading to hypersensitivity. Therefore, the use of disposable gloves and protective goggles is strongly recommended.

For further information on the safety, storage and environmental aspects concerning these products please refer to the Material Safety Data Sheet (MSDS).

Additional technical information may be obtained from our staff of the Product Management Department.

A. M. Ramp & Co. GmbH
RUCOINX Druckfarben
Lorsbacher Straße 28
65817 Eppstein/Ts.

Phone: +49 (0) 6198-304-0
Fax: +49 (0) 6198-304-3 22 88
E-Mail: info.de@inx europe.com
www.ruco-inks.com
www.inx europe.com